

Acryl FA

High-quality heat-curing resin with long liquid phase for full dentures, partial dentures and relinings.

| Features | Benefits |
|-------------------------------|---|
| Short-term hot polymerisate | Short curing time of 20 min with pressure put |
| High color stability | Homogeneous and lasting results |
| Excellent physical properties | High load capacity, also very suitable for implant supported dentures |
| Low residual monomer | Benefits allergic consumers |



Colors:

pink, pink-transparent, pink-opaque, clear (and other colors, veins separately available)

Packaging sizes: 500 g and 1000 g can, 500 ml and 1000 ml bottles

Technical data:

| | |
|-------------------|--------------------------------|
| Vickers hardness | 18 HV |
| Flexural strength | 94 MPa |
| E-Module | 2500 MPa |
| Water absorption | 20,6 $\mu\text{g}/\text{mm}^3$ |
| Water solubility | 0,6 $\mu\text{g}/\text{mm}^3$ |
| Residual Monomer | 0,8% |

Version 04/2016